

# innovus

**Decorative Products** 

## INNOVUS COLOURED MDF ECOBOARD

Non added formaldehyde coloured MDF for use in dry conditions

#### **DESCRIPTION** -

INNOVUS COLOURED MDF ECOBOARD is a robust and organic throughdyed MDF, easy to mill. The pigments used in INNOVUS COLOURED MDF ECOBOARD are introduced in an early stage of production process, where the wood fibres are carefully prepared, giving to the finished board an impressive consistency and durability of colour, resistant to light exposure.

INNOVUS COLOURED MDF ECOBOARD has very low formaldehyde emission, classified according to the rules of the official California Air Resource Board (CARB NAF) and compliant with limit of ChemVerbotsV (E05).

Regarding reaction to fire and according to EN 13986, INNOVUS COLOURED MDF ECOBOARD, with a thickness  $\geq$  9 mm and a minimum density of 600 Kg/m<sup>3</sup>, is classified as D-s2, d0 (Euroclasses definition by EN 13501-1).

In addition to technical performance INNOVUS COLOURED MDF ECOBOARD panels are sustainable and environmental friendly products.

For further information on available sizes and thicknesses, please see our Offer & Service Brochure.

#### **PROPERTIES**









LIGHT RESISTANT

PERFECT LACQUERING

VERSATILIT

ILITY EASY TO MILL





DED (

COMPLIANT WIT CHEMVERBOTSV (E05)

#### APPLICATIONS —

INNOVUS COLOURED MDF ECOBOARD is a very versatile product thus being an ideal material for designers and manufacturers, for furniture, interior design, shop fitting, milled decorative elements, wall cladding, and other creative interior applications.

Product technical characteristics make it suitable for the production of three-dimensional structures. After cutting, sanding or milling, colour will continue to shine through and surface remains stable and smooth allowing subsequent lacquering or coating.









FURNITURE

PANELIN

OFFICES &

RESTAURANT







LLNESS

RETAIL & EXHIBITION

VITCHENG

#### **RECOMMENDATIONS**-

Boards must be stacked on a hard, level surface and protected from direct contact with water. Expansion and contraction in wood products is directly related to moisture content and must be considered during design and construction.

Wood based panels are biodegradable and can be recycled, follow local regulation for the disposal of residues.

SONAE PARAUCO
Taking wood further

www.sonaearauco.com

TDS.03.01.SA.R01



### **INNOVUS COLOURED MDF ECOBOARD**

Non added formaldehyde coloured MDF for use in dry conditions

#### **GENERAL CHARACTERISTICS**

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)		
			10 - 12	>12 - 19	>19 - 25
Tolerance on thickness	EN 324-1	mm	± 0,2	± 0,2	± 0,3
Tolerance on length and width	EN 324-1	mm/m	± 2	± 2	± 2
Edge straightness tolerance	EN 324-2	mm/m	≤ 1,5	≤ 1,5	≤ 1,5
Squareness tolerance	EN 324-2	mm/m	≤ 2	≤ 2	≤ 2
Tolerance on mean density	EN 323	%	± 7	± 7	± 7
Moisture content	EN 322	%	4 - 11	4 - 11	4 - 11

#### **TECHNICAL INFORMATION -**

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)			
			10 - 12	>12 - 19	>19 - 25	
Density *	EN 323	Kg/m <sup>3</sup>	770	760	755	
Bending strength	EN 310	N/mm²	≥ 26	≥ 24	≥ 22	
Modulus of elasticity	EN 310	N/mm²	≥ 2500	≥ 2300	≥ 2200	
Internal bond	EN 319	N/mm²	≥ 0,65	≥ 0,60	≥ 0,55	
Thickness swelling 24 hours	EN 317	%	≤ 15	≤ 12	≤ 10	
Formaldehyde emission class			CARB NAF / EPA TSCA **			

INNOVUS COLOURED MDF ECOBOARD is produced with formaldehyde-free resin (NAF certified). The acronym NAF means "No-added formaldehyde" and is a classification of CARB (California Air Resources Board). It is currently the most stringent standard for formaldehyde emissions in wood-based panels. The product is also compliant with US EPA TSCA TITLE VI.

INNOVUS COLOURED MDF ECOBOARD meets the specification of EN 622, type MDF, and is CE marked. For more information regarding the technical properties, please check the product Declaration of Performance (DoP).

#### **CERTIFICATIONS**

#### Please pay attention to certified products:



The mark of responsible forestry FSC\* C009049









FSC® and PEFC™ - certified products are available on request and availability.

#### www.sonaearauco.com

#### TDS.03.01.SA.R01

All the product names and company names used in this data sheet are trade names and / or registered trademarks belonging to the respective proprietors. Any reproduction requires the express authorization of Sonae Arauco and / or the respective trademark proprietor. Sonae Arauco assumes no liability for any possible errors in this data sheet. This technical data sheet reflects the current technical specifications at the time of print and will be superseded by any new edition. The Company reserves the right to change specifications at any time without prior notification. Our detailed instructions for use must be observed. The respective building regulations must be complied with. It is important to check the material's suitability for the intended purpose.



<sup>\*</sup> Value to be used only as a reference \*\* Compliant with limit of ChemVerbotsV (E05)